

Размер зерен микропорошков, согласно стандартов FEPA, JIS, ГОСТ
(ТУ ОАО "Бокситогорский Глинозем, fepa.org, JIS R6001-1987, ГОСТ 3647-80)

редакция от 13.09.2015

MAX	MIN	FEPA	ds3	ds50max	ds50min	ds94	JIS	ds0	ds3	ds50max	ds50min	ds94	ГОСТ	ds0	ds3	ds50max	ds50min	ds94
100	40	230	82	56	50	34	240	127	103	60	54	40	M63-H	100	80	63	50	40
80	28	240	70	46,5	42,5	28	280 320	112 98	87 74	51 42,5	45 37,5	33 27	M50-H	80	63	50	40	28
63	20	280	59	38	35	22	360	86	66	37	33	23	M40-H	63	50	40	28	20
50	14	320	49	30,7	27,7	16,5	400	75	58	32	28	20						
40	10	360	40	24,3	21,3	12	500	63	50	27	23	16	M28-H	50	40	28	20	14
		600	53	41	21,5	18,5	13											
28	7	500	25	13,8	11,8	5	700 800	45 38	37 31	18,3 15	15,7 13	11 9	M20-H	40	28	20	14	10
20	5	600	19	10,3	8,3	3	1000	32	27	12,5	10,5	7						
14	3	800	14	7,5	5,5	2	1200	27	23	10,3	8,7	5,5	M10-H	20	14	10	7	5
							1500	23	20	8,6	7,4	4,5						
10	1	1000	10	5,3	3,7	1	2000	19	17	7,3	6,1	4	M7-H	14	10	7	5	3
							2500	16	14	6	5	3						
5	1	1200	7	3,5	2,5	1	3000	13	11	4,5	3,5	2	M5-H	10	7	5	3	
							4000	11	8	3,4	2,6	1,3						
3,5	0,6	1500		2,4	1,6		6000	8	5	2,4	1,6	0,8						
		2000		1,5	0,9		8000	6	3,5	1,5	0,9	0,6						

Шарабаев М.А.